

CuCoNiBe

Cobalt Nickel Beryllium Copper

Norms	Description	Applications
UNS C17500 DIN 2.1285 R.W.M.A. Class III	Strongly hardened copper alloy with high hardness and good electrical and thermal conductivity.	<ul style="list-style-type: none"> ● Spot Welding Electrodes ● Seam Welding Wheels / Discs for Stainless Steel Sheets ● Mesh Welding Electrodes ● Butt Welding Electrodes ● Plunger Tips for Cold Chamber Aluminum Die Casting ● Moulds for Non-Ferrous Metal Casting.

Chemical Composition	Mechanical Properties	Physical Properties
Co 1,1 % Ni 1,1 % Be 0.5 % Cu Balance	Hardness 220 - 260 HB Tensile Strength 700 - 900 N/mm2 Yield Strength 490 - 550 N/mm2 Elongation (L=5D) > 8 %	Electrical Conductivity min. 44 % IACS Thermal Conductivity 200 - 220 W/mK Density 8.75 g/cm3

Available Forms	Delivery Conditions
	Forged and solution heat treated.

STANDARDS & CERTIFICATION

The quality control process is certified with **UNI EN ISO 9001:2015**

In our laboratories, all products are controlled with Optical Emission Spektrometer (OXFORD INSTRUMENTS), hardness/ electrical conductivity tests with bench-type hardness measurements, mobile conductivity testers according to **DIN 3.1.B STANDARDS**.

On request We deliver our products with US Tested (second level ultrasonic report) by third-party independent laboratories

By phone

Türkiye (Turkish):
+90 (262) 503 02 12

International (English):
+90 (262) 503 40 42

Mon. – Thurs. 9:00 - 18:00 (GMT+3)
Friday 9:00 - 15:00 (GMT+3)

By mail

GM Bakır Alaşımları San. Tic. Ltd. Şti.
Dilovası OSB Mahallesi , D-4011 Sokak
Nr:22/A Gebze Kocaeli -TURKEY,
41455