

## CuAl10Fe3Mn

### Aluminum Bronze

Norms	Description	Applications
UNS C62400	High corrosion resistance and excellent hot formability for fabrication by hot forging and hot bending.	<ul style="list-style-type: none"> <li>● Bearing &amp; Bushings</li> <li>● Gears</li> <li>● Cams</li> <li>● Sleeves &amp; Guides</li> <li>● Valve Seats</li> <li>● Valve Guides</li> <li>● Gibs &amp; Slides</li> </ul>

Chemical Composition	Mechanical Properties	Physical Properties
<b>Al</b> 10 % <b>Fe</b> 3 % <b>Mn</b> 1.5 % <b>Others</b> 1 % <b>Cu</b> Balance	<b>Hardness</b> 140 - 180 HB <b>Tensile Strength</b> 650 - 750 N/mm <sup>2</sup> <b>Yield Strength</b> 350 - 380 N/mm <sup>2</sup> <b>Elongation (L=5D)</b> > 14 %	<b>Electrical Conductivity</b> min. 12 % IACS <b>Thermal Conductivity</b> 63 W/mK <b>Density</b> 7.45 g/cm <sup>3</sup>

Available Forms	Delivery Conditions
	Forged (additionally heat treated on request)

### STANDARDS & CERTIFICATION

The quality control process is certified with **UNI EN ISO 9001:2015**

In our laboratories, all products are controlled with Optical Emission Spektrometer (OXFORD INSTRUMENTS), hardness/ electrical conductivity tests with bench-type hardness measurements, mobile conductivity testers according to **DIN 3.1.B STANDARDS**.

On request We deliver our products with US Tested (second level ultrasonic report) by third-party independent laboratories

### By phone

**Türkiye (Turkish):**  
+90 (216) 394 1 666

**International (English):**  
+90 (533) 594 4 389

Mon. – Thurs. 9:00 - 18:00 (GMT+3)  
Friday 9:00 - 15:00 (GMT+3)

### By mail

**GM Bakır Alaşımları San. Tic. Ltd. Şti.**  
Istanbul Deri Organize Sanayi Bölgesi  
Tav Caddesi, M-4 Parsel, Tuzla 34956  
Istanbul-TURKEY